

Product	Color (APHA)	Specific Gravity (20°C)	Viscosity (40°C, cSt)	Viscosity (100°C, cSt)	Viscosity Index	Pour Point (°C)	Flash Point (°C)
Butyl Tallate	<13	0.875	6	2	220	-21	204
Dibutoxyethoxyethyl Adipate (DBEEA)	2 Gardner	1.012	11	3	163	-65	152
Dibutyl Maleate (DBM)	< 50	0.993 – 9964	-	-	-	-50	>141
Dibutyl Sebacate (DBS)	< 40	0.934-0.940	5.71	2.04	182	-	178
Diisodecyl Adipate (DIDA)	< 50	0.991 - 0.917	13.7	3.55	146	-68	220
Diisodecyl Phthalate (DIDP)	< 25	0.965-0.970	84	8.3	52	-48	225
Diisodecyl Sebacate (DIDS)	<100	0.907	20	5	170	-60	250
Diisononyl Adipate (DINA)	< 100	0.916-0.922	10.5	3	150	<-60	215
Diisononyl Phthalate (DINP)	< 30	0.967 - 0.977	27.7	-	-	-54	200
Dimethyl Sebacate (DMS)	< 15	0.935 – 0.939	-	-	-	23	145
Dioctyl Adipate (DOA)	< 25	0.9249	7.7	2.3	120	-75	215
Dioctyl Azelate (DOZ)	<500	0.917	11	3	135	-65	199
Dioctyl Maleate (DOM)	< 50	0.944	-	-	-	-85	185
Dioctyl Phthalate (DOP)	< 30	0.985	-	-	-	-46	207
Dioctyl Sebacate (DOS)	<50	0.908 - 0.914	11.7	3.25	155	-54	226
Dioctyl Terephthalate (DOTP)	<25	0.980-0.989	-	-	-	-50	212
Ditridecyl Adipate (DTDA)	<200	0.91	27	5	140	-50	241
Ethylhexyl Oleate (EHO)	<10	0.866	9	3	179	-32	204
Ethylhexyl Palmitate (OP)	<20	0.857	9	3	175	-4	180
Glyceryl Oleate (GMO)	2 Gardner	0.94	77	10	105	4	150
Isooctyl Tallate	<10	0.872	9	3	204	-29	227
Isopropyl Palmitate (IPP)	<15	0.852	5	2	276	14	166
Triisononyl Trimellitate (TINTM)	<70	0.976-0.982	83.7	9.92	97	-42	270
Trioctyl Trimellitate (TOTM)	<100	0.987	70	9	78	-46	258

\*This table is based on literature values, calculated values, and typical properties only. It is intended to be used for informational purposes only and does not constitute a sales specification. Please contact ChemCeed's sales department for a copy of the sales specification for a particular product listed on this table.

**WWW.CHEMCEED.COM**

1720 Prosperity Court Chippewa Falls, WI 54729  
Ph: 715.726.2300 Email: inquiry@chemceed.com