



1720 Prosperity Court
Chippewa Falls, WI 54729
www.chemceed.com

Ph: (715)726-2300
Fax: (715)726-2314
inquiry@chemceed.com

1,6-HEXANEDIOL DIGLYCIDYL ETHER

SALES SPECIFICATIONS

CAS Number: 16096-31-4

PROPERTY	LIMITS
Color APHA	60 Maximum
Viscosity mPa.s (25°C)	10-25
Epoxy Equivalent Weight g/eq	143-154
Hydrolyzable Chloride %	0.20 Maximum
Inorganic Chlorine mg/kg	50 Maximum
Moisture Content %	0.1 Maximum
Free ECH ppm	10 Maximum

05232023-AH-622