



1720 Prosperity Court
Chippewa Falls, WI 54729
www.chemceed.com

Ph: (715)726-2300
Fax: (715)726-2314
inquiry@chemceed.com

C12-14 ALKYL GLYCIDYL ETHER (C12-14 AGE)

SALES SPECIFICATIONS

CAS Number: 68609-97-2

PROPERTY	LIMITS
Color, APHA	30 Maximum
Viscosity, mPa.s (25°C)	2-10
Epoxy Equivalent Weight, g/eq	270-334
Hydrolyzable Chloride, %	0.20 Maximum
Inorganic Chlorine, mg/kg	50 Maximum
Moisture Content, %	0.10 Maximum
Free ECH, ppm	10 Maximum

05232023-AH-622