



1720 Prosperity Court
Chippewa Falls, WI 54729
www.chemceed.com

Ph: (715)726-2300
Fax: (715)726-2314
inquiry@chemceed.com

EPOXY RESIN 827

SALES SPECIFICATIONS

CAS Number: 25068-38-6

PROPERTY	LIMITS
Epoxy Equivalent Weight, g/eq	178-186
Saponifiable Chlorine, ppm	300 Maximum
Inorganic Chlorine, ppm	200 Maximum
Color, APHA	90 Maximum
Volatile Content, %	0.3 Maximum
Viscosity @25C, mPa.s	7500-10000

KG-0522023-622