



1720 Prosperity Court
Chippewa Falls, WI 54729
www.chemceed.com

Ph: (715)726-2300
Fax: (715)726-2314
inquiry@chemceed.com

EPOXY RESIN 828

SALES SPECIFICATIONS

CAS Number: 25068-38-6

PROPERTY	LIMITS
Epoxy Equivalent, g/eq	184-194
Hydrolyzable Chlorine, ppm	500 Maximum
Color, APHA	80 Maximum
Volatile Content, %	0.2 Maximum
Viscosity 25C, mPa.s	11500-14000

012122-AM-622