



1720 Prosperity Court  
Chippewa Falls, WI 54729  
[www.chemceed.com](http://www.chemceed.com)

Ph: (715)726-2300  
Fax: (715)726-2314  
[inquiry@chemceed.com](mailto:inquiry@chemceed.com)

## HYDROGENATED BISPHENOL A EPOXY RESIN

### SALES SPECIFICATIONS

CAS Number: 30583-72-3

PROPERTY	LIMITS
Color, APHA	60 Maximum
Epoxy Value, eq/100g	0.42-0.46
Epoxide Equivalent Weight, g/eq	217-238
Viscosity @25C, mPa.s	1500-4000
Hydrolyzable Chloride, %	0.20 Maximum
Inorganic Chlorine, mg/kg	50 Maximum
Moisture Content, %	0.1 Maximum
Free ECH, ppm	10 Maximum

KG-0522023-622