



1720 Prosperity Court
Chippewa Falls, WI 54729
www.chemceed.com

Ph: (715)726-2300
Fax: (715)726-2314
inquiry@chemceed.com

SOLID EPOXY RESIN 1009

SALES SPECIFICATIONS

CAS Number: 25036-25-3

PROPERTY	LIMITS
Appearance	Solid
Softening Point °C	130-150
EEW g/eq	2300-3800
Color (Gardner)	2 Maximum

05232023-AH-622