



1720 Prosperity Court  
Chippewa Falls, WI 54729  
[www.chemceed.com](http://www.chemceed.com)

Ph: (715)726-2300  
Fax: (715)726-2314  
[inquiry@chemceed.com](mailto:inquiry@chemceed.com)

## TRIMETHYLOL PROPANE TRIGLYCIDYL ETHER

### SALES SPECIFICATIONS

CAS Number: 30499-70-8

PROPERTY	LIMITS
Color, APHA	60 Maximum
Viscosity, mPa.s (25°C)	90-180
Epoxy Equivalent Weight, g/eq	136-145
Hydrolyzable Chloride, %	0.30 Maximum
Inorganic Chlorine, mg/kg	50 Maximum
Moisture Content, %	0.1 Maximum
Free ECH, ppm	10 Maximum

05232023-AH-622